

Material : ND01Z

Initial Permeability	μ_i		23°C	1.4
Saturation magnetic flux density at 8000A/m	Bs	(mT)	23°C	(9)
Relative loss factor at 230MHz	$\tan\delta/\mu_i$	($\times 10^{-6}$)	23°C	3400
Relative temp factor	$\alpha_{\mu i r}$	($\times 10^{-6}$)	20~60°C	12
Curie temperature	Tc	(°C)		---
Electrical resistivity	ρ	($\Omega \cdot m$)		10^6

