

Material : ND12S

Initial Permeability	μ_i		23°C	100
Saturation magnetic flux density at 8000A/m	B_s	(mT)	23°C	410
Relative loss factor at 1MHz	$\tan\delta/\mu_i$	($\times 10^{-6}$)	23°C	65
Relative temp factor	$\alpha_{\mu i r}$	($\times 10^{-6}$)	20~60°C	5
Curie temperature	T_c	(°C)		>250
Electrical resistivity	ρ	($\Omega \cdot m$)		10^6

