

Material : NP20D

Initial Permeability	μ_i		23°C	2000
Saturation magnetic flux density at 800A/m	Bs	(mT)	23°C	270
Relative loss factor at 100kHz	$\tan\delta/\mu_i$	($\times 10^{-6}$)	23°C	15
Relative temp factor	$\alpha_{\mu i r}$	($\times 10^{-6}$)	20~60°C	2
Curie temperature	Tc	(°C)		110
Electrical resistivity	ρ	($\Omega \cdot m$)		10^5

