

Material : NP22D

Initial Permeability	μ_i		23°C	2200
Saturation magnetic flux density at 800A/m	B_s	(mT)	23°C	260
Relative loss factor at 500kHz	$\tan\delta/\mu_i$	($\times 10^{-6}$)	23°C	15
Relative temp factor	$\alpha_{\mu ir}$	($\times 10^{-6}$)	20~60°C	3
Curie temperature	T_c	(°C)		90
Electrical resistivity	ρ	($\Omega \cdot m$)		10^5

